

# DuploCOLL® CPT 1000 F

Art. No. 11 01 90

**Pressure-sensitive adhesive film made of pure acrylic for lasting, transparent adhesive bonding**

## Product construction

|                       | Name              | Colour | Thickness [mm]       |
|-----------------------|-------------------|--------|----------------------|
| Liner                 | Polyethylene film | white  | approx. 0,11 – 0,125 |
| Adhesive covered side | Pure acrylic      |        | approx. 0,98 – 1,02  |
| Total thickness:      |                   |        | approx. 1,09 – 1,145 |

## Product advantages

- Clear bond due to highly transparent adhesive formulation: the light refraction index of DuploCOLL® CPT 1000 F is similar to that of glass.
- High stretchable and at the same time a high inner strength give DuploCOLL® CPT 1000 F an excellent resiliency within the bond
- Good initial tack, lasting ultimate bonding strength
- Good sealing, absorbing and insulating properties
- Excellent stress-absorber
- Particularly versatile, also suitable for uneven surfaces
- Highly split-resistant
- Resistant to chemicals and softeners
- Suitable for long-term use, resistant to ageing and UV radiation
- Available as perfectly fitting die-cut parts in many shapes, versions and different sizes

## Main application fields

- Bonds where maximum transparency is of central importance, for example in shower cubicles made of glass, at solar collectors and for illuminated advertising signs
- Metal-glass-connections in facade construction and apparatus engineering, as well as in the furniture industry
- Invisible bonding of different materials such as wood, aluminium, plastics, ceramics and glass

## Specific technical data\*

|   |   |
|---|---|
| Temperature range   | -40 °C to +150 °C** (up to +200 °C at short term) |
| 90° roll peel strength test on glass in accordance with DIN EN 1464 after 24 hours storage at +23 °C +/- 2 °C | 50 N/25 mm  |
| Light transmission  | > 80 % in the visible light scope                 |

\* Specific test results, statistically not approved.

\*\* Reached temperature in a rising heat test according to the internal test method PM-211 following DIN EN 1943 at 0,5 kg strength, beginning at 30 °C, increasing of temperature every 30 minutes by 10 °C.

# DuploCOLL® CPT 1000 F

Art. No. 11 01 90

**Pressure-sensitive adhesive film made of pure acrylic for lasting, transparent adhesive bonding**

## Technical Data

|   |                           |
|---|---------------------------|
| 90 ° roll peel strength test on steel in accordance with DIN EN 1464 after 24 hours storage at +23 °C +/- 2 °C                  | 80 N/25 mm                |
| Dynamic shear strength on steel in accordance with internal test method VAR-153001*** after 24 hours storage at +23 °C +/- 2 °C | 105 N/625 mm <sup>2</sup> |

\*\*\* Internal test methods are delivered on request.

## Application

|  |  |
|--|--|
| <b>Recommended application temperature</b> | 18 °C to 35 °C   |
| <b>Application guidelines</b>              | <a href="http://www.lohmann-tapes.com">www.lohmann-tapes.com</a> |

## Storage

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %).  
The storage stability is 2 years after delivery.

## Product presentation

|                               |   |  |  |  |  |
|-------------------------------|---|--|--|--|--|
| <b>Converted product</b>      | Rolls   |  |  |  |  |
| <b>Width [mm]</b>             | ≥ 6   |  |  |  |  |
| <b>Length [m]</b>             | 33  |  |  |  |  |
| <b>Max. log width: 430 mm</b> | Other dimensions, die-cuts and sheets on request. |  |  |  |  |

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

The physical characteristics contained in our data sheets represent typical or average values. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. Many factors beyond our control and uniquely within buyer's knowledge and control can affect the use and performance of our tape in a particular application. WE MAKE NO WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. Solely the buyer is responsible for determining the suitability of the specific tape for its intended use in connection with his method of application. Except where prohibited by law, we will not be liable for any loss or damage arising from the our tapes, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. Please consult our Technical Applications Department for specific advice.

Date of issue: July 2015

Lohmann GmbH & Co. KG  
Irlicher Strasse 55  
56567 Neuwied  
Germany  
Phone: + 49 (0) 26 31 34 - 0  
Fax: + 49 (0) 26 31 34 - 6661  
E-mail: [info@lohmann-tapes.com](mailto:info@lohmann-tapes.com)

For further Information  
[www.lohmann-tapes.com](http://www.lohmann-tapes.com)



Concerning product safety (confirmation, conformity to guidelines, REACH, etc.) please use the following  
E-mail address: [product.safety@lohmann-tapes.com](mailto:product.safety@lohmann-tapes.com)